


No. AP109 Certificate of Analysis

Product Name: Polyglycolide ester endcap (Mw: 10,000Da) (Lot#: 40325SMS-A)

FTIR




- Inherent Viscosity IV:**

Polymer heated to 300°C for 5 min under argon and quenched to -55°C to eliminate crystallinity. Polymer then dissolved in hexafluoroisopropanol and viscosity tested using a Cannon mini-viscometer (C286) in a 30C water bath. Average of 2 times taken and viscosity compared to literature reported values for pure HFIP at 30C to obtain inherent viscosity. Value shown +/- standard deviation.

Polymer	Inherent viscosity (g/dL)
PGA	0.25 ± 0.04

- Structure of PGA polymers**



Note: Material provided is in original crystalline form. Must be melted and rapidly quenched in order to achieve solubility.