

No. AI076 Certificate of Analysis



Product Name: Poly(lactide-co-glycolide)-*b*-Poly(ethylene glycol)-carboxylic acid endcap (M_w ~40,000-5,000 Da, 50:50 LA:GA) (Lot#: 60527DWW-A)



GPC analysis of PLGA-PEG-COOH copolymers



Analysis Method: Waters Breeze 2 system with 1 ml/min DCM flow across two Phenogel 5µm columns and one PLgel Resipore column (Agilent). Detection via refractive index, calibrated against polystyrene standards.

Polymer	M _n (from GPC)	M _w (from GPC)	PDI
PLGA-PEG-COOH	41,135	58,840	1.43
HO-PEG-COOH*	Average M _n by GFC – 4,600 Da*		

^{*-}data provided by MFG

• Structure of PLGA-PEG-COOH copolymers

$$\text{HO} - \underbrace{\left(\begin{array}{c} \text{CH}_{3} & \text{O} \\ \text{CH} - \text{C} - \text{O} \end{array} \right)}_{\text{LA}} \underbrace{\left(\text{CH}_{2} - \text{C} - \text{O} \right)}_{\text{GA}} \underbrace{\left(\text{CH}_{2} \text{CH}_{2} \text{O} \right)}_{\text{D}} - \text{CH}_{2} - \text{COOH}$$