No. AI167 Certificate of Analysis

Product Name: Poly(lactide-co-glycolide)-b-Poly(ethylene glycol)-biotin (10,000-2,000Da) Lot #210819RAI-A



H-NMR Spectrum of copolymers in CDCl3 (Bruker ≥300 MHz, PINMRF) NMR of PLGA copolymer: EG/LA-GA =52/87-82 (Mn EG/LA:GA 2291/6293:4773 Da)



FTIR Analysis: Collected from Nicollet Avatar 380 spectrometer with ATR Smart Orbit and analyzed in transmission mode.



GPC-ES Analysis Method: Waters Breeze 2 system with 1 ml/min THF flow across three GPC columns. Detection via refractive index, calibrated against polystyrene standards.

Polymer	M_n (from GPC)	M_w (from GPC)	PDI
PLGA-PEG-biotin	19,292	32,057	1.66
PEG-precursor*	2300*		

*- from MFG data

- **Structure of PLGA-PEG-biotin**



PolySciTech Division of Akina, Inc. | 3495 Kent Avenue, West Lafayette, IN 47906
765-464-0390 | www.polyscitech.com
For research use only.