

## No. AK019

## Certificate of Analysis


Product Name: Poly(lactide-co-glycolide)-b-Poly(ethylene glycol)-b-Poly (lactide-co-glycolide) copolymers (1,500-1,500, 50:50 LA:GA) (Lot# 190705RAI-A)



H-NMR Spectrum of copolymers in CDCl3 (Bruker 500 MHz, PINMRF) NMR of PLGA-PEG copolymer: EG/LA-GA = 34/20-23 (Mn EG/LA:GA 1498\*/1465-1335)




FTIR Analysis: Collected from cast-film on KBr salt-plate placed in Nicollet Avatar 320 spectrometer and analyzed in transmission mode.



GPC Analysis Method: Waters Breeze 2 system with 1 ml/min THF flow across three GPC columns. Detection via refractive index, calibrated against polystyrene standards.

Polymer	$M_n$ (from	M <sub>w</sub> (from	PDI
	GPC)	GPC)	
PLGA-PEG	5319	6555	1.23
PEG precursor*		1484*	

<sup>\*-</sup> from MFG data



Rheology performed on AR2000 (TA instruments) with 60mm 2degree cone on 20% w/v polymer in water dissolved over several days with stirring at room temperature. Viscosity of solution at 0.1 (sec $^{-1}$ ) and 5°C was measured (1minute peak hold 5 second test intervals). Rheology performed by oscillating at constant 6.283 rad/s, 0.1% strain, in increments of 1°C ranging from 5-45°C with 1 minutes of temperature equilibration at each point.

Viscosity 20% w/v solution at 5°C .02730 Pa/s

## • Structure of PLGA-PEG-PLGA triblock copolymers

