



Product Name: Poly(n-isopropylacrylamide-co-acrylamide) copolymer (95:5 NIPAM:AM)

H-NMR




FTIR



• **Rheology**

Rheology performed on AR550 (TA instruments) with 60mm 2degree cone on ~2% w/v polymer in water dissolved overnight with stirring at 4C. Viscosity of solution at 0.1 (sec-1) and 5C was measured (1minute peak hold 5 second test intervals). Rheology performed by oscillating at constant 6.283 rad/s, 0.1% strain, in increments of 2.5C ranging from 5-45C with 3 minutes of temperature equilibration at each point.

Rheology Chart



Viscosity ~2% w/v solution at 5C | 0.01417 Pa.s