


No. AP103

Certificate of Analysis




Product Name: Poly(DL-Lactide-co-caprolactone) copolymer (10:90 LA:CL, Mn: 45,000-55,000 Da) (Lot#: 250618TMT-A)

H-NMR




H-NMR Spectrum of copolymers in CDCl₃ (NMReady-60e, Nanalysis 60 MHz) NMR of P(DL)LCL copolymer: LA-CL = 14% - 86% molar ratio (LA:CL 9%:91% w:w)

FTIR



FTIR Analysis: Collected from IS5 ID7-ATR spectrometer (Thermo Scientific) and analyzed in transmission mode.

GPC-ES



Polymer	M _n (from GPC)	M _w (from GPC)	PDI
P(DL)LCL	45,043	52,643	1.17

GPC-ES Analysis Method: Waters Breeze 2 system with 1 ml/min THF flow across three GPC columns. Detection via refractive index, calibrated against polystyrene standards.


DSC

Sample: AP103 250618TMT-A
Size: 1.5000 mg
Method: Ramp

DSC

File: C:\...\COA\AP103 250618TMT-A.002

Run Date: 23-Jun-2025 11:02
Instrument: DSC Q2000 V24.11 Build 124




DSC Testing: 1-5 mg sample tested in crimped aluminum pan on a TA Instruments Model Q2000 with procedure equilibraion 100 °C, isothermal 5 minutes, equilibrate -80 °C, data on, ramp 10 °C/min to 150 °C. T_g = 40.81 °C

IV

Inherent Viscosity: 0.270 ± 0.008 dL/g (calculated from kinematic viscosity at 2% w/v Acetone on Rheosense microVISC, n=3) at 25°C.

Structure of copolymers



Approved By:
Amie Tyler
Quality Manager