


No. AP149

Certificate of Analysis




Product Name: Poly(lactic-co-glycolic) Copolymers acid end-capped (60:40 LA:GA,
Mn: 100,000- 200,000 Da) (Lot#: 250828RAI-B)

H-NMR




H-NMR Spectrum of copolymers in CDCl₃ (NMReady-60e, Nanalysis 60 MHz) NMR of PLGA copolymer: LA-GA =57%-43% molar ratio (LA:GA 63%:37% w:w)

FTIR



FTIR Analysis: Collected from IS5 ID7-ATR spectrometer (Thermo Scientific) and analyzed in transmission mode.

GPC-ES



Polymer	M _n (from GPC)	M _w (from GPC)	PDI
PLGA	101,280	144,083	1.42

GPC-ES Analysis Method: Waters Breeze 2 system with 1 ml/min THF flow across three GPC columns. Detection via refractive index, calibrated against polystyrene standards.


DSC

Sample: AP149 250828RAI-B
Size: 3.5000 mg
Method: Ramp

DSC

File: C:\...\COA\AP149 250828RAI-B.001

Run Date: 03-Sep-2025 15:17
Instrument: DSC Q2000 V24.11 Build 124




DSC Testing: 1-5 mg sample tested in crimped aluminum pan on a TA Instruments Model Q2000 with procedure equilibraion 100 °C, isothermal 5 minutes, equilibrate -80 °C, data on, ramp 10 °C/min to 150 °C. T_g = 47.02 °C

IV

Inherent Viscosity: 0.412 ± 0.033 dL/g (calculated from kinematic viscosity at 2% w/v Acetone on Rheosense microVISC, n=3) at 25°C.

Structure of copolymers



Approved By:
Amie Tyler
Quality Manager