


No. AP202

Certificate of Analysis




Product Name: Poly(lactic-co-glycolic) copolymers ester endcap (75:25 LA:GA)
(M_n : 85,000-100,000 Da) (Lot#: 250401TMT-A)

H-NMR




H-NMR Spectrum of copolymers in $CDCl_3$ (NMReady-60e, Nanalysis 60 MHz) NMR of PLGA copolymer: LA-GA =71%-29% molar ratio (LA:GA 76%:24% w:w)

FTIR



FTIR Analysis: Collected from IS5 ID7-ATR spectrometer (Thermo Scientific) and analyzed in transmission mode.

GPC-ES



Polymer	M _n (from GPC)	M _w (from GPC)	PDI
PLGA	89,084	125,245	1.41

GPC-ES Analysis Method: Waters Breeze 2 system with 1 ml/min THF flow across three GPC columns. Detection via refractive index, calibrated against polystyrene standards.


DSC

Sample: AP202 250401TMT-A
Size: 3.7000 mg
Method: Modulate-no-eqb

DSC

File: C:\...\COA\AP202 250401TMT-A DSC.001

Run Date: 10-Apr-2025 12:12
Instrument: DSC Q2000 V24.11 Build 124




DSC Testing: 1-5 mg sample tested in crimped aluminum pan on a TA Instruments Model Q2000 with procedure equilibraion 100 °C, isothermal 5 minutes, equilibrate -80 °C, data on, ramp 10 °C/min to 150 °C. Tg = 45.09 °C

IV

Inherent Viscosity: 0.514 ± 0.023 dL/g (calculated from kinematic viscosity at 2% w/v Acetone on Rheosense microVISC, n=3) at 25°C.

Structure of copolymers



Approved By:
Amie Tyler
Quality Manager