


No. VP002

Certificate of Analysis

Product Name: Poly(lactide-co-glycolide-co-graft-poly(ethylene glycol)) PLGA-g-PEG (75:25 LA:GA, Mn 1500 - 3500, molar PEG content: 40 - 60%) (Lot#: 250211RAI-A157)




H-NMR




H-NMR Spectrum of copolymers in CDCl₃ (Bruker ≥ 300 MHz, PINMRF) NMR of PLGA-g-PEG copolymer:
LA:GA:EG = 2.7 : 1 : 3.4

FTIR



FTIR Analysis: Collected from IS5 ID7-ATR spectrometer (Thermo Scientific) and analyzed in transmission mode.


GPC-ES



Polymer	M _n (from GPC)	M _w (from GPC)	PDI
PLGA-g-PEG	2158	4107	1.90

GPC-ES Analysis Method: Waters Breeze 2 system with 1 ml/min THF flow across three GPC columns. Detection via refractive index, calibrated against polystyrene standards.

RHEOLOGY



Rheology performed on AR2000 (TA instruments) with 60mm 2degree cone on 30% w/v polymer in PBS dissolved over 24 hours with stirring at 4°C. Viscosity of solution at 0.1 (sec⁻¹) and 5°C was measured (1 minute peak hold 5 second test intervals). Rheology performed by oscillating at constant 6.283 rad/s, 0.1% strain, in increments of 1°C ranging from 5-45°C with 1 minutes of temperature equilibration at each point.

Viscosity 30% w/v solution at 5°C	0.01204 Pa/s
Gelation onset temperature	27.2C

Structure of copolymers

